

3

CLIPPEDIMAGE= JP408041434A

PAT-NO: JP408041434A

DOCUMENT-IDENTIFIER: JP 08041434 A

TITLE: ACRYLIC ADHESIVE COMPOSITION

PUBN-DATE: February 13, 1996

INVENTOR-INFORMATION:

NAME

NUMATA, NORIO

FUKUOKA, MASATERU

ASSIGNEE-INFORMATION:

NAME

SEKISUI CHEM CO LTD

COUNTRY

N/A

APPL-NO: JP06182071

APPL-DATE: August 3, 1994

INT-CL (IPC): C09J133/06;C09J133/06 ;C09J007/02

ABSTRACT:

PURPOSE: To obtain the solution type acrylic adhesive composition capable of being cured at low temperatures in a short time and excellent in the balance of physical properties.

CONSTITUTION: The acrylic adhesive composition comprises 100 pts.wt. of an acrylic copolymer comprising 60-99.9wt.% (based on the whole amount of monomers) of one or more (meth)acrylate esters of a formula:  
 $\text{CH} \begin{smallmatrix} \text{>} 2 \end{smallmatrix} \text{<}/\text{SB} \text{>} = \text{CR} \begin{smallmatrix} \text{>} 1 \end{smallmatrix} \text{<}/\text{SP} \text{>} = \text{COOR} \begin{smallmatrix} \text{>} 2 \end{smallmatrix} \text{<}/\text{SP} \text{>} \text{ (R} \begin{smallmatrix} \text{>} 1 \end{smallmatrix} \text{<}/\text{SP} \text{>} \text{ is hydrogen or methyl group; R} \begin{smallmatrix} \text{>} 2 \end{smallmatrix} \text{<}/\text{SP} \text{>} \text{ is 4-14C alkyl group), 1-20 pts.wt. of a 2-12C low molecular compound having one or more carboxyl groups in the molecule or 5-20 pts.wt. of a tackifying resin having one or more carboxyl groups and one or more abietine skeletons in the molecule, and 0.05-3 pts.wt. of a multifunctional carbodiimide compound.}$

COPYRIGHT: (C)1996,JPO